



TOPCon N-TYPE M 1 0

BAUER SOLARTECHNIK

COMMERCIAL

BS-144M10HBW-GG 575 - 585 W

BIFACIAL GLASS-GLASS HALF-CELL MODULE



















GRADE "A" N-TYPE BIFACIAL HALF CELLS

Only Grade "A" half-cells are used in the production of all BAÚER solar modules and only the blackest are selected. Up to 30% increase in yield through bifacial cells active on both sides and a glass backside.



LOW LIGHT PERFORMANCE

Stronger performance in low lighting conditions than PERC modules, such as overcast days, mornings and evenings helping to ensure a higher energy output than PERC every day.



STABILITY & DURABILITY

2 x 2 mm tempered anti-reflective solar glass; dirt-repellent, scratch-resistant, durable and shock-proof.



CERTIFICATION

Constant in-house quality controls - certified several times over by accredited inspection bodies.



FIRE CLASS A

Maximum fire protection through double glazing according to the highest security requirements.



WARRANTY & GUARANTEE

30 year product warranty and a linear performance guarantee ovér a period of 30 years.



GERMAN GUARANTOR

If necessary, it is guaranteed that a German company takes over any claim settlements.



REINSURANCE COVERAGE


BAUER is re-insured with Munich RE for 15 years of the product warranty & 30 years of the performance guarantee.




BAUER GUARANTEE ①


Our extended guarantee covers the module guarantee and a lump-sum compensation for the replacement of a defective module (Guarantee conditions as of 01.12.2023).

BAUER guarantees a minimum performance value of 87.4% after 30 years for the **COMMERCIAL** glass-glass solar modules.










PHYSICAL SPECIFICATIONS

Module dimensions	2278 x 1134 x 35 mm	
Weight	32.7 kg	
Frame	Black anodized aluminum profile	
Frontside	AR-coating semi-toughened glass, 2 mm	
Embedding material	EVA	
Backside	White-glazed & semi-toughened glass, 2 mm	
Solar cells	144 monocrystalline N-type bifacial half-cells	
Bifaciality	80 % ± 10 %	
Junction box(es)	IP68, 3 bypass diodes	
Cable & connector	1x4 mm², 1300 mm, Stäubli MC4/EVO2A	

BAUER SOLARTECHNIK

COMMERCIAL

BS-144M10HBW-GG 575 - 585 W



30 year product warranty

30 year performance guarantee

OPERATING CONDITIONS

BS-580-144M10HBW-GG

580

 $0 \sim +3$

51.44

14.37

42.70

13.60

22.45

638 (+58)

696 (+116) 754 (+174)

Operating temperature	-40 to 85°C
Static load	5400 Pa (snow/wind/ice)
Hail test	Ø 25 mm at ~ 23 m/s

CERTIFICATION

IEC 61215,61730-1/2,61701(Salt mist),62716(Ammonia) CSA; Fire Class: A (USA); UL Type 29

PACKAGING

Modules per pallet	30
Pallets/modules per truck	20/600

BS-585-144M10HBW-GG

585

 $0 \sim +3$

51.65

14.44

42.92

13.65

22.65

643.5 (+58.5) 702 (+117)

760.5 (+175.5)

BS-575-144M10HBW-GG	
Pmax (W)	575
Pmax (%)	0 ~ +3
Voc (V)	51.26
Isc (A)	14.31
Vmpp (V)	42.53
Impp (A)	13.54
ηm (%)	22.26
10 % Pmpp (W)	632.5 (+57.5)
20 % Pmpp (W)	690 (+115)
30 % Pmpp (W)	747.5 (+172.5)
NOCT (°C)	45 +/- 2
Tk (Voc)	-0.26 %/°C
Tk (Isc)	+0.046 %/°C
Tk (Pmpp)	-0.30 %/°C
(V)	1500
(A)	30
	Pmax (W) Pmax (%) Voc (V) Isc (A) Vmpp (V) Impp (A) ηm (%) 10 % Pmpp (W) 20 % Pmpp (W) NOCT (°C) Tk (Voc) Tk (Isc) Tk (Pmpp) (V)

¹Nominal value is specified in the written warranty conditions. A possible light-induced degradation in performance is not taken into account.

 2 Values under Standard Test Conditions (STC): air pressure 1.5 AM, irradiance 1000 W/m², cell temperature 25°C. STC measuring tolerance: ± 3 % (Pmax), ± 10 % (Vmax, Impp, VOC, ISC). The beneficiary under the reinsurance policy is solely Bauer Solar Engineering GmbH. Please contact us to get information on how this insurance coverage benefits you as a customer. Note: please read th installation manual before using this product. Subject to change.

© 2024 Bauer Solar Engineering GmbH. Effective: 01/12/24.